

# Antique

Upholstery Leather

spinneybeck




**Antique brings an  
elegance that  
never gets old.**

Antique is a select chromium tanned, aniline dyed, enhanced grain leather. The select lower Alpine hides required to produce Antique are derived from northern Italy, southern Germany, and Switzerland. The special retannage adds to the enrichment of the leather and provides a smooth, tight grain and suppleness of hand, which approximates España leather. The methods and processes used to produce Antique are essentially the same as those used in the production of España.


Through the use of advanced finishing techniques, the surface of this product is lightly antiqued to produce an elegant patina reminiscent of gracefully aged leather. Antique features a unique breathable protective finish, which is impregnated into the leather, becoming an integral part of the material.

<b>Product</b>	Antique (AQ)
<b>Content</b>	European cowhide
<b>Origin</b>	Italy
<b>Hide Size</b>	50–55 sq ft (4.6–5.1 sq m)
<b>Thickness</b>	0.9–1.0 mm
<b>Weight</b>	2.25–2.5 oz / sq ft (687–763 g / sq m)
<b>Grain</b>	Enhanced
<b>Grain Texture</b>	Smooth, tight
<b>Tannage</b>	Chrome
<b>Dye</b>	Aniline
<b>Finish</b>	Medium
<b>Primary Uses</b>	Upholstery, handrails, rugs, wall panels, architectural applications
<b>Industry</b>	Automotive, contract, healthcare, hospitality, marine, residential
<b>Maintenance</b>	Wipe with a cool, damp cloth. For tougher soiling, use a pH-balanced soap and rinse. Repeat, if needed. Occasional use of Spinneybeck Finished Leather Cleaner, Conditioner & Protector is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
<b>Custom</b>	Custom colors not available
<b>Special Services</b>	Flame treatment and perforated available with an upcharge
<b>Colorfastness to Light</b>	Class 4
<b>Colorfastness to Crocking</b>	Class 4–5 (dry), Class 4 (wet)
<b>Flammability</b>	ASTM E 84: Class A (flame treated) Boston Fire Dept BFD IX-1: Pass (flame treated) BS EN1021 (Part I and Part II): Pass BS 5852 Crib 5 and Crib 7: Pass (flame treated) CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent (flame treated) Cigarette Ignition Resistance NFPA 260: Class 1 FAR 25.853(a) 60 sec vertical burn, 12 sec vertical burn. Oil burner-fire block: Pass IMO Resolution A.652 (16): Pass (flame treated) IMO Resolution A.653(16) Part 2 and 5: Pass (flame treated) NF P 95 512 1986 (Electric Burner Test): Class M1 (flame treated)
<b>Durability + Strength</b>	Abrasion ASTM D 7255: 1,000+ cycles (CS-10 wheels) Breaking Force ASTM D 2208: 150 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: 70,000 flexes Tearing Strength ASTM D 4705: 25 lb


#### Standard Colors




AQ 0023




AQ 0025




AQ 0024



AQ 0022



AQ 0021



AQ 0027