


# Cervo

Upholstery Leather

spinneybeck




**Cervo has a  
luxurious hand.**


In Italian, the word Cervo translates to “deer.” This word personifies the luxurious hand that approximates the suppleness of deerskin. The unique tannage and specialized softening create a pronounced pebble grain characteristic in premium hides originating from Scandinavia. A blend of the finest quality aniline dyes provides excellent lightfastness properties for a naked leather, surpassing industry standards. Cervo also receives a greater saturation and dye enrichment than ordinary upholstery leathers.

<b>Product</b>	Cervo (CV)
<b>Content</b>	European cowhide
<b>Origin</b>	Italy
<b>Hide Size</b>	50–55 sq ft (4.6–5.1 sq m)
<b>Thickness</b>	1.4–1.6 mm
<b>Weight</b>	3.5–4.0 oz / sq ft (1068–1221 g / sq m)
<b>Grain</b>	Full
<b>Grain Texture</b>	Raised pebble
<b>Tannage</b>	Chrome
<b>Dye</b>	Aniline
<b>Finish</b>	Very light
<b>Primary Uses</b>	Upholstery, handrails, wall panels, architectural applications
<b>Industry</b>	Contract, hospitality, marine, residential
<b>Maintenance</b>	Wipe entire surface with a soft cloth and cool water to even out any abrasions or stains. Do not spot rub, for it will darken only that area. Occasional use of Spinneybeck Aniline Leather Cleaner, Conditioner & Protector is recommended. Other leather cleaners such as saddle soap or household cleaners that may contain harsh chemicals, alcohol or ink removers should never be used.
<b>Custom</b>	Custom colors available on a select basis
<b>Special Services</b>	Perforated available with an upcharge
<b>Variation</b>	Class 3
<b>Colorfastness to Light</b>	Class 4 (dry)
<b>Colorfastness to Crocking</b>	Class 2–3 (dry)
<b>Flammability</b>	BS EN1021 (Part I and Part II): Pass CAL 117: Pass CAL 133: Successfully used in CAL 133 applications with Firegard F187 fire backer material or equivalent Cigarette Ignition Resistance NFPA 260: Class 1
<b>Durability + Strength</b>	Abrasion ASTM D 7255: n/a Breaking Force ASTM D 2208: 500 lb Elongation ASTM D 2211: 30–50% at 50 lb Flex ASTM D 2097: n/a Tearing Strength ASTM D 4705: 50 lb


#### Standard Colors




CV 0040




CV 0042




CV 0043




CV 0044



CV 0048



CV 0050



CV BLCK